

## G430RL | Open Cell Polyether Polyurethane Foam

### Technical Data Sheet

Physical Property	Value (US Standard)	Value (Metric)
Cell Structure	Open	Open
Density	4.3 ±10% lb/ft <sup>3</sup>	68.8 ±10% kg/m <sup>3</sup>
Tensile Strength	50 psi	345 kPa
Elongation	120%	120%
Indentation Force Deflection		
25% Deflection	180 lbs/50 in <sup>2</sup>	990 N/323 cm <sup>2</sup>
65% Deflection	400 lbs/50 in <sup>2</sup>	2225 N/323 cm <sup>2</sup>
Retention of Tensile Strength after 5 hours, 105 C, Steam Autoclave	Min. 70%	

Flammability Characteristics:  
Meets S4.3 FMVSS No. 302.

Features:  
 May be flame laminated  
 Meets Requirements of ROHS June, 2013 Revision of SVHC 2011/65/EU  
 Compliant with european Union REACH - EC1907/2006