Rapid Die Cut

Fluoroelastomer (Viton)

TECHNICAL DATA SHEET | (EFFECTIVE 24FEB25)

75 Durometer, General Purpose

PHYSICAL PROPERTY	TEST METHOD	UNIT	VALUE
Hardness (Shore A)	ASTM D2240	-	75 +/- 5
Tensile Strength	ASTM D412	psi	1200 min.
Elongation	ASTM D412	%	250 min.
Compression Set	ASTM D395B	%	50 max.
Color		-	Black
Fluid Resistance	ASTM D471	%	30 max.
Specific Gravity	ASTM D792	nominal	1.92

© 2025 Rapid Die Cut. All Rights Reserved.