Rapid Die Cut

Fluoroelastomer (Viton), Specification Grade

Virgin Viton™ fluoroelastomer is defined as polymer supplied by The Chemours Company, and processed by a licensed Chemours Company Viton™ manufacturer, no scrap, re-grind, or reprocessed fluoroelastomer compound shall be added to it.

TECHNICAL DATA SHEET | (EFFECTIVE 24FEB25)

55 Durometer, ASTM

PHYSICAL PROPERTY	TEST METHOD	UNIT	VALUE
Hardness (Shore A)	ASTM D2240	-	75 +/- 5
Tensile Strength	ASTM D412	psi	1600 min.
Elongation	ASTM D412	%	150 min.
Compression Set	ASTM D395B	%	15 max.
Specific Gravity	ASTM D792	nominal	1.86
Color		-	Black

© 2025 Rapid Die Cut. All Rights Reserved.