



Medium Grade Silicone Foam

Medium open cell silicone foam offers the lightness of foam with the enhanced sealing capabilities of sponge rubber. Its compact cell structure and unique formulation provide enhanced sealing against penetration from fine particles and wind-driven rain and fire.

TECHNICAL DATA SHEET | (EFFECTIVE 26FEB21)

Medium Grade Silicone Foam			
PHYSICAL PROPERTY	TEST METHOD	UNIT	VALUES
Cellular Structure	--	--	Open Cell
Firmness	--	--	Medium
Density		lb/ft ³ (kg/m ³)	22 (352)
Compression Deflection, 25%	ASTM D1056	psi (kPa)	9.7 (67)
Compression Set	ASTM D1056 212°F (100°C)	%	2.4 < 5
Tensile Strength	ASTM D412	psi (kPa)	35 (240)
	ASTM D751	psi (kPa)	30 (207)
Tensile Elongation	ASTM D412	%	45
Water Absorption	--	%	0.5 < 5
Flame Resistance	UL 94 (File E83967) V-0	--	Meets
Flame Spread Index (1s)	ASTM E162 Flaming Mode < 35	--	Meets
Smoke Density (D _s)	ASTM E662 Flaming Mode, 1.5 min, <100 Flaming Mode, 4.0 min, <200	--	Meets
Burn Length	FMVSS 302 <100 mm/min	--	Meets
Toxic Gas Emission Rating	SMP-800-C @ 1.5/4.0 min	--	Meets
Total Mass Loss	ASTM E595 @ (4×10 ⁻⁶ Torr)	%	0.98

Medium Grade Silicone Foam

PHYSICAL PROPERTY	TEST METHOD	UNIT	VALUES
Collected Volatile Condensable Materials (CVCM)	ASTM E595 @ (4×10 ⁻⁶ Torr)	%	0.25
Water Vapor Regain	ASTM E595 @ (4×10 ⁻⁶ Torr)	%	0.03
Recommended Constant Use	--	°F °C	-67 - +392 -55 - +200
Thermal Conductivity	ASTM C518	W/m °K	0.009
Low Temperature Flex	ASTM D1056 @ -67°F (-55°C)	--	Meets
Low Temperature Brittleness	ASTM D745 @ -67°F (-55°C)	--	Meets
Dielectric Strength	ASTM D149	Vols/mil	75
Dielectric Constant	ASTM D150	1 kHz	1.7
Dissipation Factor	ASTM D150	1 kHz	0.005
Dry Arc Resistance	ASTM D495	Seconds	125
Volume Resistivity	ASTM D257	Ohm-cm	10 ¹⁴
Industry Standards			
FDA Regulation 21 CFR 177.2600	Rubber articles intended for repeated use ≥ 0.8mm thickness Type2, Meets MATSPC		
UL-94 V0 & HBF HF-1			
General Motors GMW 16392			