



KLINGERSIL® C-4401, Universal Gasket

KLINGERSIL® C-4401 is manufactured with aramid fiber reinforced with a nitrile binder. This general purpose gasket material has excellent sealability and chemical resistance, making it suitable for a wide range of applications.

TECHNICAL DATA SHEET | (EFFECTIVE 26FEB21)

KLINGERSIL® C-4401, Universal Gasket

PHYSICAL PROPERTY	TEST METHOD	UNIT	VALUE
Color	--	--	Green or White
Composition	Aramid fiber reinforced with a nitrile binder		
Creep Relaxation	ASTM F38B (1/32")	%	20
Sealability	ASTM F37A (1/32")	ml/hr	<0.25
Gas Permeability	DIN 3535/6	ml/min	<0.5
Compressibility	ASTM F36J	%	7 - 14
Recovery	ASTM F36J	% minimum	50
KLINGER Hot Compression Test			
Thickness Decrease	73°F (23°C)	% initial	14
Thickness Decrease	572°F (300°C)	% additional	17
Weight Increase after Immersion in:			
Fuel B, 5h/73°F (23°C)	ASTM F146	% maximum	10
Thickness Increase after immersion in:			
ASTM Oil IRM 901, 5h/300°F (149°C)	ASTM F146	%	0 - 5
ASTM Oil IRM 903, 5h/300°F (149°C)			0 - 5
ASTM Fuel A, 5h/73°F (23°C)			0 - 5
ASTM Fuel B, 5h/73°F (23°C)			0 - 10
Dielectric Strength	ASTM D149-95a	kV/mm	14
Density	ASTM F1315	lb/ft³ (g/cc³)	112 (1.8)
Leachable Chloride Content	FSA Method	ppp	100
Line Call Out	ASTM F104	--	F712121B3E12K6M5